

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 6357 (1971): Sulphated oil for leather fat liquoring
[CHD 17: Leather, Tanning Materials and Allied Products]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



Indian Standard
SPECIFICATION FOR
SULPHATED OIL FOR LEATHER
FATLIQUORING

(First Reprint SEPTEMBER 1977)

UDC 675.045.5:665.382



© Copyright 1972

INDIAN STANDARDS INSTITUTION
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

Price Rs. 8.00

Gr 3

April 1972

Indian Standard

SPECIFICATION FOR SULPHATED OIL FOR LEATHER FATLIQUORING

Leather Sectional Committee, CDC 16

Chairman

DR Y. NAYUDAMMA

Representing

Council of Scientific & Industrial Research, New Delhi

Members

SHRI R. K. AGARWAL	Leather Research & Testing Laboratory, Kanpur
SHRI H. R. GADI (Alternate)	
SHRI A. S. BHATTACHARYA	Directorate General of Ordnance Factories, Calcutta
SHRI S. SAMPATH (Alternate)	
SHRI R. A. BHOTE	Directorate of Marketing & Inspection, Nagpur
SHRI T. G. BOBADE	Ministry of Defence (R & D)
SHRI A. NAGAPPA CHETTIAR	Leather Export Promotion Council, Madras
SHRI T. ABDUL WAHID (Alternate)	
SHRI O. P. DHAMIJA	Export Inspection Council of India, Calcutta
SHRI T. N. GANJWAR	Indian Leather Corporation Limited, Madras
SHRI J. GHOSH	The State Trading Corporation of India Ltd, New Delhi
SHRI N. KANNAN	Ministry of Defence (DGI)
SHRI W. G. EDGER (Alternate)	
SHRI P. U. K. MENON	Gordon, Woodroffe & Co (Madras) Pvt Ltd, Madras
SHRI G. P. MADHAVAN (Alternate)	
SHRI K. V. S. MURTHI	Planning Commission, New Delhi
SHRI S. NAGARAJAN	Development Commissioner, Small Scale Industries, New Delhi
SHRI S. P. SINGARAM (Alternate)	
PRINCIPAL	College of Leather Technology (Government of West Bengal)
SHRI S. RAJA	The Tanner, Bombay
SHRI T. RAJAGOPAL RAO	The Associated Tanners, Vizianagaram
SHRI G. ROY CHOUDHURY	Export Promotion Council for Finished Leather & Leather Manufactures, Kanpur
SHRI B. D. SENGUPTA (Alternate)	
SHRI N. R. SARKAR	Bata Shoe Co Pvt Ltd, Calcutta
SHRI P. K. SARKAR	Indian Leather Technologists' Association, Calcutta
SHRI SANJOY SEN	The National Tannery Co Ltd, Calcutta
SHRI J. SINHA ROY (Alternate)	
SHRI B. P. SENGUPTA	Directorate General of Supplies & Disposals (Inspection Wing), New Delhi
SHRI A. T. BASAK (Alternate)	

(Continued on page 2)

INDIAN STANDARDS INSTITUTION
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

(Continued from page 1)

Members

*SHRI R. SNEBERGER
SHRI P. R. SONDI

SHRI R. R. SONDI (Alternate)
SHRI N. R. SRINIVASAN

SHRI Z. KHALIDI (Alternate)
SHRI R. THANJAN

SHRI R. S. GHOSH (Alternate)
SHRI D. DAS GUPTA,
Director (Chem)

Representing

The Tanners' Federation of India, Kanpur
Kapurthala Northern India Tanneries Ltd,
Kapurthala

Tannery & Footwear Corporation of India Ltd,
Kanpur

Directorate General of Technical Development,
New Delhi

Director General, ISI (Ex-officio Member)

Secretary

SHRI S. DAS GUPTA
Assistant Director (Chem), ISI

Leather Auxiliaries Subcommittee, CDC 16:8

Convener

SHRI M. A. GHANI

Central Leather Research Institute (CSIR), Madras

Members

SHRI A. GANESAN (Alternate to
Shri M. A. Ghani)

SHRI B. B. BAGALKOTE
SHRI T. G. BOBADE
Dai-ichi Karkaria Pvt Ltd, Bombay
Ministry of Defence (R & D)

SHRI B. S. KADAM (Alternate)
SHRI N. P. DAS
SHRI N. KANNAN
Chika Ltd, Bombay
Ministry of Defence (DGI)

SHRI W. G. EDGER (Alternate)
SHRI S. C. NANDY
Bata Shoe Co Pvt Ltd, Calcutta

SHRI T. P. DHAR ROY (Alternate)
SHRI NASIM IQBAL
The Tanners' Federation of India, Kanpur
Leather Chemicals & Industries Ltd, Calcutta

SHRI S. SARBADHIKARI
SHRI P. C. MONDAL (Alternate)
SHRI E. S. SUBRAMANIAN
Handymain's Industries Ltd, Madras

SHRI P. SRINIVASAN (Alternate)
SHRI N. VISWANATHAN
BASF India Ltd, Bombay

SHRI M. L. DASGUPTA (Alternate)

*Shri R. Sncberger is also alternate to Shri N. R. Sarkar.

Indian Standard

SPECIFICATION FOR SULPHATED OIL FOR LEATHER FATLIQUORING

0. FOREWORD

0.1 This Indian Standard was adopted by the Indian Standards Institution on 27 October 1971, after the draft finalized by the Leather Sectional Committee had been approved by the Chemical Division Council.

0.2 Sulphated oils are used in fatliquoring operation during tanning to provide flexibility to the leather. Fatliquors are generally prepared with sulphated oils, raw oils and other additives.

0.3 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS : 2-1960*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This standard prescribes the requirements, methods of sampling and test for sulphated oils used in the leather industry for fatliquoring.

1.1.1 This specification covers only sulphated oils of marine and vegetable origin exclusive of any further additives or blends of fatliquors made thereof.

2. TERMINOLOGY

2.1 For the purpose of this standard, the definitions given in IS : 548-1964† and IS : 1640-1960‡ shall apply.

3. REQUIREMENTS

3.1 Physical Condition — The material shall be a free-flowing, clear, oily liquid. Appearance of any graininess or a slight physical separation

*Rules for rounding off numerical values (*revised*).

†Methods of sampling and test for oils and fats (*revised*).

‡Glossary of terms relating to hides, skins and leather.

like a liquid and semi solid portion appearing specially in winter season or long storage shall not be considered as defect so long as the two portions individually or together form ready emulsions in water.

3.2 Emulsion Characteristics — The emulsion shall satisfy the following requirements:

- a) The product shall form a ready emulsion in hot or cold water in any dilution.
- b) An emulsion containing 3 percent total fatty material shall remain stable for at least 30 minutes at $27 \pm 2^\circ\text{C}$ without creaming or separation.
- c) The sulphated oils shall be capable of being readily washed out with water without leaving any oily feeling to hand.
- d) The sulphated product when mixed with 25 percent raw oil(s) having an acid value not above 10, or other mineral oil shall form a ready emulsion when diluted with hot/cold water in all dilutions.

3.3 Odour — The product shall be free from rancid or putrefactive odour of the oils.

3.4 Chemical Requirements — The product, besides meeting the other characteristics mentioned above, shall also meet the chemical requirements mentioned in Table 1.

TABLE 1 CHEMICAL REQUIREMENTS

Sl No.	CHARACTERISTIC	REQUIREMENT	METHODS OF TEST, REF TO CLAUSE IN APPENDIX A
(1)	(2)	(3)	(4)
i)	Moisture, percent by mass, <i>Max</i>	35	A-2
ii)	pH of emulsion	6.5 to 8.0	A-3
iii)	Total fatty matter, percent by mass	60	A-4
iv)	Unsaponifiable matter, percent by mass, <i>Max</i>	2	A-5
v)	Total alkalinity in mg equivalent per 10 g, <i>Max</i>	3	A-6
vi)	Organically combined sulphates (SO_3) as sulphuric esters, percent by mass, <i>Min</i>	3	A-7
vii)	Total organically combined sulphates (SO_3) as sulphuric and sulphonc esters, percent by mass, <i>Min</i>	4.5	A-7 and A-8
viii)	Ash, percent by mass, <i>Max</i>	3	A-9

3.5 Keeping Quality — The product shall be stable for at least 6 months when stored in normal packings.

4. PACKING AND MARKING

4.1 Packing — The material after manufacture shall be packed in air-tight containers which shall not develop any rust or deterioration of the product due to the presence of water in the medium or any of the ingredients used in the formulation.

4.2 Marking — The containers shall be marked with the name of the manufacturer, trade-mark, if any; batch number; date of manufacture; and the quantity in litres.

4.2.1 The containers may also be marked with the ISI Certification Mark.

NOTE — The use of the ISI Certification Mark is governed by the provisions of the Indian Standards Institution (Certification Marks) Act and the Rules and Regulations made thereunder. The ISI Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well-defined system of inspection, testing and quality control which is devised and supervised by ISI and operated by the producer. ISI marked products are also continuously checked by ISI for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the ISI Certification Mark may be granted to manufacturers or processors, may be obtained from the Indian Standards Institution.

APPENDIX A

(Table 1)

TEST METHODS

A-1. QUALITY OF REAGENTS

A-1.1 Unless specified otherwise, pure chemicals and distilled water (*see* IS : 1070-1960*) shall be used in tests.

NOTE — ' Pure chemicals ' shall mean chemicals that do not contain impurities which affect the results of analysis.

A-1.2 Water to be used for tests other than chemical tests (3.4, Table 1) shall conform to IS : 4221-1967†.

A-2. DETERMINATION OF MOISTURE

A-2.1 Outline of the Method — The percentage of water present is determined by distillation with a solvent.

*Specification for water, distilled quality (*revised*).

†Quality tolerance for water for leather industry.

A-2.2 Procedure — Heat 30 g of the oil and 70 ml of a solvent in a 300 ml flask connected, preferably by ground glass connections, to a condenser and a Dean and Stark receiving tube or similar apparatus graduated in divisions of 0.1 ml. Add a few glass beads to the flask to prevent bumping, but conduct the distillation in such a manner that the contents of the flask are in vigorous movement. Continue the distillation until the liquid falling from the condenser is clear, then disconnect the receiving tube, allow to stand and read off the volume of water which has separated from the solvent.

NOTE 1 — For sulphated castor oil, toluene or xylene are the preferred solvents. For other oils a light petroleum fraction boiling between 100 and 140°C is suitable.

NOTE 2 — Thorough cleaning of the apparatus with chromic-sulphuric acid mixture, followed by thorough washing with water prevents the formation of troublesome drops of water difficult to get into the measuring tube.

NOTE 3 — This method is not accurate if the sulphated oil contains mineral acids, free sulphonic acids or free sulphuric esters, alcohol, acetone or other water miscible solvents.

NOTE 4 — If ammonia is present, the specific gravity of the aqueous layer should be determined and taken into account in the calculation.

A-2.3 Calculation — Calculate the percentage of water present in the sample from the reading and the weight of the oil taken for the test.

A-3. DETERMINATION OF pH

A-3.1 Determine the pH electrometrically, with the help of pH meter using glass electrodes.

NOTE — As the pH of solution of sulphated oils varies with the temperature, this should be controlled during the tests, and in some cases it may be necessary to make the determination at 50°C.

A-4. DETERMINATION OF TOTAL FATTY MATTER

A-4.0 Follow the procedure given in Method A or Method B.

A-4.1 Procedure

A-4.1.1 Method A — If inorganic salts or soaps are present, heat 3.5 g of the sample with 10 ml of 25 percent hydrochloric acid under a reflux condenser until the fat separates out clearly and free from emulsion. Cool and add 50 ml diethyl ether. If any fatty matter is present in the condenser, wash it down into the flask with ether. If after a brief shaking, the upper ethereal layer is not clear, repeat the operation with longer heating with hydrochloric acid. Run the solution of fat and the acid wash-water into a separating funnel, run off the acid aqueous layer and when the ether layer is clear, wash with 10-percent sodium chloride (NaCl) until free from acid. If water-soluble fatty acids are present as in oils such as coconut and palm kernel, extract the combined aqueous layers

again with ether. If other substances which are split by hydrochloric acid (HCl) only with difficulty are present (alkaline earth soaps, filling materials, etc), repeat the treatment with hydrochloric acid. If emulsions form, which prevent sharp separation, remove the material responsible for the formation of the emulsions by filtration and wash with ether. Dry the combined ether solutions for half an hour over anhydrous sodium sulphate, having first rendered the sodium sulphate fat free by washing with dry ether. Filter the dried ethereal solution of the fat into a weighed flask. Distill off the greater portion of the ether and remove the final traces by blowing over the surface, preferably with a hand blower. The solvent rapidly evaporates and constant weight is rapidly attained by heating at 100°C. The weight may be taken as constant if it falls by not more than 0.1 percent during 15 minutes heating.

NOTE 1 — In the case of fats such as tallow, containing high-melting-point fatty acids, it is not convenient to dry off the ether in this manner. The residual water in this case may be removed readily by heating on a water-bath after the addition of 2 to 3 ml acetone to the ethereal solution.

NOTE 2 — If the fat contains volatile fatty acids, for instance, palm kernel, or coconut oil, the drying is done at 60°C.

NOTE 3 — Easily oxidised fats (drying, semi-drying, fish oils, etc) are dried in a stream of inert gas or in a partial vacuum.

A-4.1.2 Method B — Where it is desired to extract the fat without pre-treatment with hydrochloric acid, dissolve 3.5 g of the sample in 10 ml diethyl ether. Dry the ethereal solution over fat-free anhydrous sodium sulphate in a ground glass stoppered flask, to facilitate shaking, for 30 minutes and filter. If the ether insolubles are required, filter the ethereal solution before drying. Then follow the procedure given in **A-4.1.1**.

NOTE — The ether extract contains the saponifiable fatty matter (neutral fat and free fatty acids) and the other ether soluble materials, such as natural and added unsaponifiable matter, resins, naphthenic acid, and fatty acids combined with bases carried through with the ether in small amounts only.

A-5. DETERMINATION OF UNSAPONIFIABLES

A-5.1 Determine the unsaponifiables following the procedure given in 8 of IS : 548-1964*.

A-6. DETERMINATION OF TOTAL ALKALINITY

A-6.1 Procedure — Dissolve 10 g of the sample in 100 ml of water in a conical flask, warming if necessary, to obtain solution. After cooling, add

*Methods of sampling and test for oils and fats (revised).

30 g of sodium chloride, 25 ml of ether and 5 drops of 0.1 percent methyl orange indicator and titrate with 0.5 *N* sulphuric acid until the aqueous layer is orange. Stopper the flask and shake the contents frequently during the titration, and calculate as follows:

$$A = \frac{10 V N}{W}$$

where

A = total alkalinity in milligrams equivalent per 10 g of oil,

V = volume in millilitres of sulphuric acid,

N = normality of sulphuric acid, and

W = weight in grams of the sample.

NOTE — The method is not applicable in the presence of sodium acetate or other compounds which are not accurately titratable to methyl orange in aqueous solution.

A-7. DETERMINATION OF ORGANICALLY COMBINED SO₂ AS NEUTRALIZED SULPHURIC ESTER

A-7.1 Apparatus

A-7.1.1 *Conical Flask* — with ground glass neck, 250 ml capacity.

A-7.1.2 *Splash Head*

A-7.1.3 *Liebig Condenser*

A-7.2 Reagents

A-7.2.1 *Sulphuric Acid* — approximately *N*, accurately standardized.

A-7.2.2 *Sodium Hydroxide* — approximately *N*, accurately standardized.

A-7.2.3 *Sodium Chloride*

A-7.2.4 *Diethyl Ether*

A-7.2.5 *Methyl Orange Indicator* — 0.1 percent aqueous solution.

A-7.3 Procedure — Weigh 10 g of the sample into a 250-ml conical flask. Add 30 ml sulphuric acid accurately from a burette, and a few glass beads. Attach splash head and condenser. Boil for one and a half hours or until both oil and water layers are perfectly clear. Allow to cool. Wash down condenser and splash head with 10 ml water. Disconnect. Add 50 ml water, 30 g sodium chloride (NaCl), 25 ml diethyl ether and 5 drops methyl orange indicator. Titrate with sodium hydroxide with shaking until the aqueous layer is of the same intermediate colour as in the determination of total alkalinity. Run a blank and titrate it also after refluxing.

A-7.4 Calculation

A-7.4.1 Calculate organically combined sulphate (SO_3) existing as neutralized sulphuric esters expressed as milligrams equivalent per 10 g of oil as follows:

Organically combined SO_3 as neutralized sulphuric esters, milligrams equivalent per 10 g of oil, $G = A + F$

where

A = total alkalinity in milligrams equivalent per 10 g of oil (see A-6.1); and

F = increase in acidity on boiling, in milligrams equivalent per 10 g of oil and is calculated as follows:

$$F = \frac{(V_1 - V_2) N}{W} \times 10$$

where

V_1 = volume in millilitres of sodium hydroxide required in the titration of the blank,

V_2 = volume in millilitres of sodium hydroxide required in the titration of the sample,

N = normality in N of sodium hydroxide solution, and

W = weight in grams of the sample taken.

Note — If F is negative, retain the sign of the above equation.

A-7.4.2 Calculate organically combined sulphate (SO_3) existing as neutralized sulphuric esters expressed as a percentage on the original sample as follows:

Organically combined sulphate (SO_3)

$$\begin{aligned} \text{as sulphuric esters, percent by mass} &= (A + F) \times 0.80066 \\ &= (A + F) \times 0.8007 \\ &= G \times 0.8007 \end{aligned}$$

A-8. DETERMINATION OF TOTAL ORGANICALLY COMBINED — SO_3 AS SULPHURIC AND SULPHONIC ESTERS

A-8.1 Determine the organically combined sulphates (SO_3) existing as neutralized sulphuric esters as in A-7.

A-8.2 Determine the organically combined sulphates (SO_3) existing as neutralized sulphonic esters as in A-8.2.1.

A-8.2.1 Weigh about 2 g of the sample into a platinum dish and add 25.0 ml of 0.1 N sodium hydroxide. Evaporate the mixture to dryness on the water bath and heat in an oven at 100-105°C for one hour or longer if slow drying. Then ignite by placing the basin on a pipe clay triangle

in a muffle furnace at a dull red heat (500 — 550°C) for 30 minutes. Remove the basin from the muffle furnace, allow to cool and add 5 ml of 30 percent hydrogen peroxide to oxidize any bisulphite formed and heat in a muffle furnace again (350°C) for 30 minutes. Remove the basin from the muffle, allow to cool and thoroughly wash out with hot distilled water into a beaker. Add 25 ml of 0.1 *N* sulphuric acid (H_2SO_4), boil the solution down to about 50 ml to expel carbon dioxide, and allow to cool. Titrate with 0.1 *N* sodium hydroxide using five drops of 0.1 percent methyl orange as indicator until the colour turns yellow.

A-8.3 Calculation

A-8.3.1 Calculate the organically combined sulphates (SO_2) existing as neutralized sulphonic esters *I* as follows:

First step:

$$T = \frac{(X - Y)}{W} \times 10$$

where

T = resultant acidity expressed as milligrams equivalent sodium hydroxide per 10 g of oil;

X = milligrams equivalent alkali used = $(25 \times N_1) + (\text{titre value} \times N_1)$, where N_1 is the normality in *N* of sodium hydroxide solution;

Y = milligrams equivalent acid used = $(25 \times N_2) + VN_2$, where *V* = volume in millilitres of any additional sulphuric acid added, and N_2 = normality of sulphuric acid; and

W = weight in grams of the sample.

Second step:

$$I = (T - F) \text{ milligrams equivalent per 10 g of oil} \\ = (T - F) \times 0.80066 \text{ percent.}$$

NOTE — In case of ammonia, neutralized oils

$$I = (T - F - T_1) \text{ milligrams equivalent per 10 g of oil} \\ = (T - F - T_1) \times 0.80066 \text{ percent}$$

where

T = resultant acidity expressed as milligrams equivalent sodium hydroxide per 10 g of oil (see First step);

F = increase in acidity in milligrams equivalent per 10 g of oil (see A-7.4.1); and

*T*₁ = milligrams equivalent ammonium salts per 10 g of oil and is determined as follows:

2 g of sample is boiled with 50 ml of 0.1 *N* alcoholic KOH and the ammonia distilled into 100 ml of saturated boric acid solution containing

the indicator (mix indicator solutions of 0.06 percent methyl red and 0.04 percent methylene blue in 96 percent ethyl alcohol and take 2 ml of the mixed indicator solution in 1 litre of water). The distillate is treated with 0.2 *N* hydrochloric acid

$$T_1 = \frac{VN \times 10}{W}$$

where

V = volume in millilitres of hydrochloric acid,

N = normality of hydrochloric acid, and

W = weight in grams of the sample.

NOTE — If *T* and *F* are negative, retain the sign in the equations.

A-8.3.2 Total organically combined sulphates (SO_3) expressed as milligrams equivalent per 10 g of oil consists of the sum of the percentage got in **A-7.4.1** and **A-8.3.1**.

A-9. DETERMINATION OF TOTAL ASH

A-9.1 Weigh 3 g of oil in a platinum dish and heat gently until a charred residue remains. Extract this with hot water to remove soluble salts, filter through a low ash filter paper and wash thoroughly. Ash the filter paper and charred residue, moistening with ash-free hydrogen peroxide, if difficulty is experienced. Allow the dish to cool, add the aqueous extract and evaporate on a steam bath. Finally complete the ashing at as low a temperature as possible. Cool the dish and weigh.

INTERNATIONAL SYSTEM OF UNITS (SI UNITS)

Base Units

Quantity	Unit	Symbol
Length	metre	m
Mass	kilogram	kg
Time	second	s
Electric current	ampere	A
Thermodynamic temperature	kelvin	K
Luminous intensity	candela	cd
Amount of substance	mole	mol

Supplementary Units

Quantity	Unit	Symbol
Plane angle	radian	rad
Solid angle	steradian	sr

Derived Units

Quantity	Unit	Symbol	Conversion
Force	newton	N	1 N = 1 kg.m/s ²
Energy	joule	J	1 J = 1 N.m
Power	watt	W	1 W = 1 J/s
Flux	weber	Wb	1 Wb = 1 V.s
Flux density	tesla	T	1 T = 1 Wb/m ²
Frequency	hertz	Hz	1 Hz = 1 c/s (s ⁻¹)
Electric conductance	siemens	S	1 S = 1 A/V
Pressure, stress	pascal	Pa	1 Pa = 1 N/m ²

INDIAN STANDARDS INSTITUTION

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

Telephone : 27 01 31 (20 lines)

Telegrams : Manaksanstha

Regional Offices:

			Telephone
Western :	Novelty Chambers, Grant Road	BOMBAY 400007	37 97 29
Eastern :	5 Chowringhee Approach	CALCUTTA 700072	23-08 02
Southern :	C.I.T. Campus, Adyar	MADRAS 600020	41 24 42

Branch Offices:

'Pushpak', Nurmohamed Shaikh Marg, Khanpur	AHMADABAD 380001	2 03 91
'F' Block, Unity Bldg, Narasimharaja Square	BANGALORE 560002	2 76 49
Ahlmsa Bldg, SCO 82-83, Sector 17C	CHANDIGARH 160017	2 83 20
5-8-56/57 Nampally Station Road	HYDERABAD 500001	4 57 11
117/418 B Sarvodaya Nagar	KANPUR 208005	82 72
B.C.I. Bldg (3rd Floor), Gandhi Maldan East	PATNA 800004	5 36 55
Hantex Bldg (2nd Floor), Rly Station Road	TRIVANDRUM 695001	32 27